



ELX

General Trading LLC

Report Of Test Result

Sample place:	company	Bitumen Grade:	vg20
Delivery Date:			
Test Date:			
Report Date:			
Sample code:			
Ambient Condition:			
Temperature (°C): 25	Peressure (KPa): 101	Humidity (%): 54	

Test Result

No.	Tests Title	Result	Standard Range		Tests Method	
			ASTM D3381/INSO12505-2		ASTM	INSO
			Min	Max		
1	Viscosity @60 °C, 300 mm Hg, Pa.s	208	160	240	D2171	12851
2	Kinematic Viscosity @135°C	363	210	**	D2170	12855
4	Penetration @25 °C	60	40	**	D5	2950
6	Solubility in T.C.E %	99.98	99	**	D2042	2953
7	Flash point, °C	316	230	**	D92	1175
6	Sp.Gr@25 °C	1.0154	REPORT		D70	3872
7	Spot test , by Naphta	neg	Neg		AASHTO T102	2949
8	Penetration Index	-0.56	-1.5	1	-	

Test on residue After TFOT

9	Viscosity @60 °C , 300 mm Hg, Pa.s	598.7	**	1000	D2171	12851
10	Ductility @ 25°C, cm	62	20	**	D113	3866

Note:

Approved ☒ Not Approved ☐